Appl. No. 10/722,157

13:46

Amdı. Dated June 7, 2006

Reply to Office Action of March 8, 2006

Attorney Docket No. 81863.0024 Customer No.: 26021

Amendments to the Specification:

Please replace the paragraph beginning at page 18, line 20, with the following rewritten paragraph:

and merging to p of pag 19

3, line 20, with the hard of pag 19

Invention preferably SVP on sisting of alumina, 3.19.07

th layer compound The supporting member 101 used in the present invention preferably cont:uns a crystal of at least one kind selected from the group consisting of alumina, beryllia, zirconia, magnesia, mullite, spinel structure, bismuth layer compound, compound of tungsten bronze structure, compound of Ph-based perovskite structure, compound of niobium-based perovskite structure and compound of tantalum-based percyskite structure. These materials are materials that have the same quality as that of the piezoelectric pile, or have poor reactivity. Therefore, the reaction with the green sheet is suppressed, thus making it possible stabilize characteristic of the piezoelectric pile.